



SPECIFICATION SHEET

ZN 60

Zinc-Based Thread Compound for All Rotary Shouldered Connections

COLOR	Gray
PENETRATION	290 - 310 (ASTM D 217)
WEIGHT/GALLON	16.3 pounds/gallon
DROPPING POINT	350°F/177°C (typ)
FLASH POINT	385°F/196°C (min)
BRUSHABLE TO	10°F/-12°C
SERVICE RATING	350°F/177°C
TORQUE FACTOR	1.0 (per API RP 7A1)*
CONTAINS	Zinc and other nonmetallic additives

Zn 60 is a zinc-based thread compound made with finely powdered metallic zinc. It contains 60% zinc as well as H₂S and oxidation inhibitors. Meets the requirements of API RP SPEC 7: "Specification for Rotary Drill Stem Elements".

RECOMMENDED FOR - tool joints, drill collars, and drilling and coring bits.

*API RP 7A1: "Recommended Practice for Testing of Thread Compound for Rotary Shouldered Connections"

NOTE: Due to operation and equipment variables, this value may require adjustment based on field experience.

BESTOLIFE ZN 60 MEETS ALL APPLICABLE API AND IADC STANDARDS.

A MATERIAL SAFETY DATA SHEET IS AVAILABLE FROM THE MANUFACTURER.
DO NOT USE ON OXYGEN LINES OR IN OXYGEN ENRICHED ATMOSPHERES.